




Optical grade fused quartz JGS2 – sample thickness: 2,0 mm



Inner transmission values of fused quartz JGS2 at selected wavelengths per 2,0 mm layer.

$\lambda$ [nm]	200	210	220	240	254	280	500	2200	2700
Transmittance [%]	64,092	71,874	82,149	82,008	87,245	91,404	92,323	93,312	92,311