


CG di Conti Gloriana

Transimission curve



Chemical composition

| Al | Fe | K | Na | Li | Ca | Mg | Cu | Mn | Pb | B | Ti |
|----|-----|-----|-----|-----|-----|-----|-----|-----|-------|------|-----|
| 20 | 1.0 | 3.5 | 3.5 | 1.0 | 2.0 | 0.5 | 0.3 | 0.5 | <0.01 | <0.2 | 2.0 |

Physical properties

| | |
|---|---------------------|
| Density 20°C kg*m ⁻³ (×10 ³) | 2.2 |
| Coefficient of expansion 25-300°C °C ⁻¹ (×10 ⁻⁶) | 0.56 |
| Softening point (°C) | 1710 |
| Annealing point (°C) | 1230 |
| Strain point(°C) | 1140 |
| Youngs modulus(Pa) | 7.3×10 ⁵ |